

## AquaSeal PEX-A Plumbing Pipe

JOB		REPRESENTATIVE	
ENGINEER		ORDER #	DATE
CONTRACTOR		SUBMITTED BY	DATE
PAGE #		APPROVED BY	DATE

Qty/Length	Part #	Pipe OD	SDR	Comments
			11	
			11	

### PEX-A Large Diameter Plumbing Pipe Non Barrier

The AquaSeal Pex-A pipes are produced from special HMW-HDPE resins. The crosslinking is performed (peroxide method) during the production process, resulting in irreversible cross-links between adjacent P.E. chains. The crosslinking process renders the pipe improved mechanical process such as; resistance to corrosion and pressure at high temperature, exceptional high abrasion and superb chemical resistance, and excellent longevity at high temperatures. Product is uncoated in Natural color and is covered by a twenty-five year manufacturers warranty.



Technical Data	Value	Unit	Test Standard
Density	938	kg/m <sup>3</sup>	ASTM F-876
Impact Strength (at 20°C) (at 100°C)	No Failure No Failure	KJ/m <sup>2</sup> KJ/m <sup>2</sup>	DIN 53453
Elongation at break (at 20°C) (at 100°C)	350-550 500-700	%	DIN 53455
Tensile Strength (at 20°) (at 100°C)	20-26 9-13	N/mm <sup>2</sup> N/mm <sup>2</sup>	DIN 53455
Pressure Temperature Characteristics	203°F @ 87 PSI (95°C @ 6 bar)  68°F @ 217.5 PSI (20°C @ 15 bar)		
Pressure Tested	290 PSI (20bar)		

Manufacturing Standards	
ASTM	F-876/F-877
ASTM	F-2023 Chlorine
ASTM	E-84
CSA	B137.5/LM101713
DIN	4726/9
IAPMO	C
ICBO	ES ER-5258
NSF	61

Description	OD mm	OD in	SDR	Part #	Weight lbs/ft	Wall Thickness in	Length/ft
PEX-A Non Barrier Pipe (*)	40	1-1/4"	11	94040	.282	.146	1
PEX-A Non Barrier Pipe (*)	50	1-1/2"	11	94050	.437	.181	1
PEX-A Non Barrier Pipe (*)	63	2"	11	94063	.692	.228	1
PEX-A Non Barrier Pipe (*)	90	3"	11	94090	1.49	.323	1
PEX-A Non Barrier Pipe (*)	110	4"	11	94110	2.09	.394	1

(\*) Sold per foot, please specify length